

AS-164

13/16" X 15/8"

14 Gauge Channel

Stocked in pre-galvanized, plain, powder coated Supr-Green, zinc trivalent, PVC coated & aluminum, in 10 & 20 ft. lengths. Note: Also available in Stainless Steel 304 & 316 Alloys. Other materials, finishes & lengths are available upon request.





GENERAL


ALL-STRUT channels are manufactured by a series of forming dies, or rolls, which progressively cold work the strip steel into the desired channel configuration. This method produces a cross section of uniform dimensions within a tolerance of plus or minus 0.015", on outside dimensions.


LENGTH INFORMATION

ALL-STRUT channels are produced and stocked in 10' and 20' lengths with a tolerance of $\pm \frac{1}{8}$ ". Other lengths are available upon request.

LOADING DATA

- 1. When calculating load at center of span, multiply load from table by 0.5 and deflection by 0.8.
- 2. When calculating beam and column loads for aluminum, multiply by 33%.





MATERIAL

ALL-STRUT channels are produced from prime structural steel covered by the following specifications. (See technical section for additional information)

- ☐ Pre-Galvanized Steel. ASTM A-653
- ☐ Plain Steel ASTM A-1011-04-SS
- □ Aluminum (Type 6063T6)...... ASTM B-221
- ☐ Stainless Steel (Type 304 & 316) . . ASTM A-240 Other materials and specifications available on request.
- ☐ Hot Dipped Galvanized. ASTM A-123
- ☐ Zinc Trivalent Chromium. ASTM B-633-85
- ☐ Powder Coated Supr-Green ASTM B-117
- □ PVC Coating 40 ML Thickness Available Upon Request




AS-164

¹³/₁₆" X 1⁵/₈"

14 Gauge Channel

SECTION PROPERTIES

Catalog No.	Wt./Ft. Lbs.	Area of Section Sq. In.		X-X Axis		Y-Y Axis			
			I in⁴	S in ³	r in.	l in⁴	S in ³	r in.	
AS-164	1.03	0.294	0.027	0.058	0.303	0.110	0.135	0.612	



I = Moment of Inertia

S = Section Modulus

r = Radius of Gyration

	Static Beam Load (X-X Axis)							Column Loading Data				
Span or Unbraced Height (In)	Max Allowable Uniform Load (Lbs)	Deflection at Uniform Load (In)	Uniform Load at Deflection				Max. Allowable Load at	Max. Column Load Applied at C.G.				
			Span/180 Deflection (Lbs)	Span/240 Deflection (Lbs)	Span/360 Deflection (Lbs)	Weight of Channel (Lbs)	Slot Face (Lbs)	k=.65 (Lbs)	k=.80 (Lbs)	k=1.0 (Lbs)	k=1.2 (Lbs)	
12	970	0.03	970	970	970	1.0	2,010	6,500	6,340	6,090	5,820	
18	640	0.06	640	640	520	1.5	1,890	6,120	5,820	5,410	5,010	
24	480	0.11	480	440	300	2.1	1,740	5,690	5,270	4,700	3,980	
30	390	0.17	380	280	190	2.6	1,590	5,240	4,700	3,800	2,930	
36	320	0.25	260	200	130	3.1	1,420	4,790	3,980	2,930	2,050	
42	280	0.33	190	140	100	3.6	1,250	4,200	3,270	2,170	1,510	
48	240	0.44	150	110	70	4.1	1,090	3,620	2,600	1,660	1,150	
60	190	0.68	90	70	50	5.2	830	2,520	1,660	1,060	**	
72	160	0.98	70	50	30	6.2	650	1,750	1,150	**	**	
84	140	1.34	50	40	20	7.2	**	1,280	**	**	* *	
96	120	1.75	40	30	20	8.2	**	**	**	**	**	
108	110	2.21	30	20	10	9.3	**	**	**	**	**	
120	100	2.73	20	20	NR	10.3	**	**	**	**	**	
144	80	3.93	20	NR	NR	12.4	**	**	**	**	**	
168	70	5.34	NR	NR	NR	14.4	**	**	**	**	**	
180	60	6.13	NR	NR	NR	15.5	**	**	**	**	**	
192	60	6.98	NR	NR	NR	16.5	**	**	**	**	**	
216	50	8.83	NR	NR	NR	18.5	**	**	**	**	**	
240	50	10.91	NR	NR	NR	20.6	**	**	**	**	**	

Bearing Load may limit load

NR = Not Recommended

Notes

2. Allowable beam loads are based on a uniformly loaded, simply supported beam. For capacities of a beam loaded at midspan at a single point, multiply the beam capacity by 50% and deflection by 80%.

3. The above chart shows beam capacities for strut without holes. For strut with holes, multiply by the following:

OS by 88%, RS (% holes) by 88%, KO by 82%,

OS3 by 90%, RS-3/4-MOD (3/4 holes) by 85%,

^{**} Not recommended - KL/r exceeds 200

^{1.} The beam capacities shown above include the weight of the strut beam. The beam weight must be subtracted from these capacities to arrive at the net beam capacity.